Studio 54 2966

Acoustic



760.599.3985 Sales@SoundAway.com

Studio 54 2966

Acoustic

Specifications

Content 100% polypropylene

Weight 12.8 ± 1.0 oz./lin. yd.

Width 66" min. useable

Repeat .1" vertical, none horizontal

Treatment polyester binder

Cleaning Code

W-S. May be cleaned with a 4:1 water-to-bleach solution. Rinse well after cleaning.

Performance

Colorfastness to Light (AATCC 16 Option 3) Grade 4 min. at 40 hours

Grade 4 min. at 40 hours
Colorfastness to Crocking (AATCC 8)

Grade 4 min. dry & Grade 3 min. wet Breaking Strength (ASTM D5034) 100 lbf min. warp and 250 lbf min. fill


100 lbf min. warp and 250 lbf min. fill *** Flammability (ASTM E84)**

Flammability (ASTM E84) Class I or A

Acoustical Performance

The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

Acoustical Performance for Panel Applications (ISO 10534-2)



NRC of anechoic termination 1.00

NRC of fabric in front of anechoic termination .95

Miscellaneous

Colors may vary slightly between dye lots. This is a directional fabric. Application testing of this product is recommended. Variation in texture and luster, due to the manufacturing process, is to be expected and is part of the inherent beauty of Studio 54.

Visit SoundAway.com or call to request samples.

