Lido 2858


Oak Bluffs



Newport 030



Cape May



Moonstone 015




Hermosa



Yellowstone 067



Green Bay



Balboa 019



Smith Point



Bryce Canyon



Padre 052



Huron 055



Huntington



Heartland 064



Pine Valley



Napa Valley

Lido 2858

Specifications

52% pre-consumer recycled polyester 48% post-consumer recycled polyester
11.5 ± 1.0 oz./lin. yd.
66" min. useable
none


Cleaning Code

Standard Care Label W-S. Clean with water based cleaning agents, foam or pure, water free solvents. Vacuuming or light brushing is recommended to prevent dust and soil buildup. May also be disinfected with hydrogen peroxide, alcohol, and quaternary ammonium (quat) based cleaners.

Acoustical Performance

The plot below summarizes impedance tube measurements of absorption of an anechoic termination and various fabrics in front of the anechoic termination.

Acoustical Performance for Panel Applications (ISO 10534-2)



NRC of anechoic termination 1.00 NRC of fabric in front of anechoic termination .95

Performance

**	Colorfastness to Light (AATCC 16.3 Option 3) Grade 4 min. at 40 hours
0	Colorfastness to Crocking (AATCC 8) Grade 4 min. dry & Grade 3 min. wet
<u></u>	Breaking Strength (ASTM D5034)

100 lbf min. warp and 125 lbf min. fill

Flammability (ASTM E84) Class I or A

Sustainability





Miscellaneous

Proudly woven in North America supporting our local communities.

Application testing of this product is recommended. Colors may vary between dye lots. This is a directional fabric.

This pattern is included in the underwriters laboratory panel fabric recognition program. Additional testing of this U.L. recognized component fabric is not required on approved panels from participating manufacturers.

*Certification Marks owned by the Association for Contract Textiles, Inc



